



TYPICAL REPAIR METHOD FOR A CUT 2x3 OR 2x4 BOTTOM CHORD, NO PIPE

SITUATION BEFORE REPAIR



SITUATION AFTER REPAIR



Wood grade of the chord to repair	Wood grade of the piece of wood to add
Triforce G-14 (SPF #1 / #2)	SPF #1 / #2
Triforce G-15 (MSR SPF 1650fb-1.5E)	SPF #1 / #2
Triforce G-18 (MSR SPF 2100fb-1.8E)	MSR SPF 1650fb-1.5E
Triforce G-20 (MSR SPF 2400fb-2.0E)	MSR SPF 1650fb-1.5E

RTF-012-20

IMPORTANT NOTICES

If you can't make the repair as specified, please contact the manufacturer at the contact information above.

PL Premium Glue: Refer to Lepage manufacturer for recommendations and restrictions applicable to its use.

Before adding loads and/or moving the joist, the cure time specified by the glue manufacturer must be respected.

Check out the www.openjoisttriforce.com website for the latest updates.

